

NCC COMPLIANT AS5216 CONFORMING

CHEMICAL CAPSULE EPOXY ACRYLATE

Range M8 - M24

Zinc Plated Studs
Dry, internal applications

FEATURES & BENEFITS

- Ideal for safety critical applications.
- Intended working life of 50 years.
- No mess, no waste - 1 capsule per hole.
- ETA rating - Option 7, Uncracked Concrete.
- Ideal for close to edge & close anchor spacing applications.
- Fast cure times

APPLICATIONS/TRADES

- Structural steel connection to concrete.
- Plant room equipment hold down.
- Hand rails.
- Steel framing.
- Machinery hold down.

COMPLIANCE




AS5216




OPTION 7
Uncracked Concrete



Convenient external hex drive head with driver bit included



Correct install depth mark on stud aligns with concrete surface



Chisel point ensures thorough mixing of chemical during install



CHEMICAL CAPSULE

EPOXY ACRYLATE


NCC COMPLIANT | AS5216 CONFORMING

RANGE


Chemical Anchor Stud - Product Code	Pack Qty	Thread size	Anchor length (mm)	Drill hole Ø (mm)	Drill hole depth (mm)	Minimum concrete thickness (mm)	Maximum fixture thickness (mm)	Fixture clearance hole Ø (mm)
			l_t	d_o	h_1	h_{min}	$t_{fix, max}$	d_f
ACSMZ081102	10	M8	110	10	80	110	15	9
ACSMZ101302	10	M10	130	12	90	120	20	12
ACSMZ121602	10	M12	160	14	110	140	25	14
ACSMZ161902	10	M16	190	18	125	160	35	18
ACSMZ202602	5	M20	260	25	170	220	50	22
ACSMZ243002	5	M24	300	28	210	260	55	26

Chemical Capsule - Product Code	Product Description	Pack Qty	Drill hole Ø (mm)	Drill hole depth (mm)
			d_o	h_1
ACCMP080002	Chemical Capsule M8	10	10	80
ACCMP100002	Chemical Capsule M10	10	12	90
ACCMP120002	Chemical Capsule M12	10	14	110
ACCMP160002	Chemical Capsule M16	10	18	125
ACCMP200002	Chemical Capsule M20	6	25	170
ACCMP240002	Chemical Capsule M24	6	28	210


INSTALLATION




Drill hole into substrate to the specified diameter and depth.




Clean the hole using the following sequence with a blower pump and correctly sized wire / nylon brush: Blow, brush, blow, brush, blow. Protect the hole from contamination prior to completing the installation.



Insert capsule into clean hole.



Using a power tool and the driver bit supplied with the studs, rotate & drive the anchor stud into the capsule until the anchor stud bottoms out in the hole. Stop driving and remove tool / driver at this point. **PROTECT THE ANCHOR FROM DISTURBANCE UNTIL THE CURE TIME HAS ELAPSED.**



Once the cure time has elapsed, place the fixture and clamp it down using a wrench to tighten to the specified installation torque.

CHEMICAL CAPSULE

EPOXY ACRYLATE

NCC COMPLIANT | AS5216 CONFORMING

PRODUCT INSTALL & PERFORMANCE INFORMATION

Chemical Anchor Stud - Product Code	Anchor length (mm)	Maximum fixture thickness (mm)	Drill hole depth (mm)	Minimum concrete thickness (mm)	Socket size AF (mm)	Installation torque (Nm)	Design Capacities	
							Uncracked concrete - tension (kN)	Uncracked concrete - shear (kN)
	l_t	$t_{fix, max}$	h_1	h_{min}	SW	T_{inst}	N_{Rd}	V_{Rd}
ACSMZ081102	110	15	80	110	13	10	12.0	7.2
ACSMZ101302	130	20	90	120	17	20	19.3	11.2
ACSMZ121602	160	25	110	140	19	40	26.7	16.8
ACSMZ161902	190	35	125	160	24	80	40.0	31.2
ACSMZ202602	260	50	170	220	30	120	60.0	48.8
ACSMZ243002	300	55	210	260	36	180	80.0	70.4

Note: Concrete cylinder compressive strength = 32MPa.
 Single anchor capacity - no nearby edge, minimum recommended concrete thickness.
 For combined load cases (tension & shear) - must also comply with $(N^* / N_{Rd}) + (V^* / V_{Rd}) \leq 1.2$.

Important Disclaimer: Product performance information contained herein is based on ETA certificate data and AS5216:2021 inputs as appropriate. Capacity information is limited to very simple load case configurations and is provided to enable a relative comparison within and across product ranges. The design of an anchoring solution for a particular application should be conducted by an appropriately qualified design professional.

MINIMUM CURING TIMES

Temperature in the concrete substrate	Minimum curing time - dry concrete hole	Minimum curing time - wet concrete hole
$\geq 0^\circ\text{C}$	5 hours	10 hours
$\geq +5^\circ\text{C}$	1 hour	2 hours
$\geq +20^\circ\text{C}$	20 minutes	40 minutes
$\geq +30^\circ\text{C}$	10 minutes	20 minutes

Whilst every care was taken in the preparation of this publication, Bremick® accepts no responsibility for the accuracy of the information supplied. Bremick® reserves the right to make alterations to product specifications as part of ongoing product development and improvement. This publication serves as a guide and it's the responsibility of the end user to ensure product suitability for their application. The contents of this publication are the exclusive copyright of Bremick® and may not be reproduced without permission.